

Anchor Wire CuZn37 (Ms63)

Material based on a CuZn - alloy for anchor wire

Norms CEN/TS 13388 : CuZn37 CW508L

EN 12166 : CuZn37 CW508L ASTM : UNS C27000

Composition (weight %) Cu : 62,0 – 64,0

Zn : balance Others : max. 0,5

Physical properties

kg/dm³ Density (20°C) : 8,4 ° C Melting range : 902 - 920 Modulus of elasticity kN/mm² : 110 W/m⋅ K Thermal conductivity : 121 Coefficient of linear expansion (20°C-300°C) : 20,2 x·10⁻⁶ 1/ K $m/\Omega \cdot mm^2$ Conductvity : 14,5 – 15,5 Ω ·mm²/m Resistivity : 0,0645 - 0,0690

Surface

Bright

Profiles

Round profile

Flat profile (ungrooved / single-sided grooved / double-sided grooved)

Make up

Available in spools

Materials used in contact with foodstuff

The requirements of "Technical Guide on Metals and alloys used in food contact materials, CoE (2013)" are fulfilled.

Migrations tests have been made according to following standards:

- DIN EN 13130-1:
 - Guide to test methods of material and articles in contact with foodstuff
- DIN EN ISO 17294-2, DIN EN ISO 11885 (E22) + DIN EN ISO 17852 (E 35):
 Methods for determination of chemical elements

The tests showed that migration of following chemical elements were below the limits of determination:

Aluminium, Anitmony, Arsenic, Barium, Cadmium, Chromium, Cobalt, Copper, Iron, Lead, Lithium, Managnese, Mercuri, Molybdenum, Nickel, Silver, Thalium, Tin, Titanium, Vanadium, Zinc.

www.bedra.com

Version: 06/2017. Copyright Berkenhoff GmbH. Errors and technical modifications excepted